

TRANSFER & WASH CONDITIONS

STANDARD PRODUCTS

PRINTABLES PRODUCTS

		POLI-FLEX® PREMIUM	POLI-FLEX® BLOCKOUT	POLI-FLEX® NYLON	POLI-FLEX® STRETCH	POLI-FLEX® SPORT	POLI-FLEX® TURBO	TUBITHERM	TUBITHERM NEON COLOURS	POLI-FLEX® 5001 BLOCKOUT WHITE	POLI-FLEX® IMAGE REFLEX SILVER 4781 / REFLEX ECO 4782	POLI-FLEX® 4214 / 4215 DIMENSION	POLI-FLEX® IMAGE BRILLANT 421 / 431	POLI-FLEX® IMAGE LUMINOUS	POLI-FLEX® PEARL GLITTER	POLI-FLEX® IMAGE PAINT / GLOSSY	POLI-FLEX® IMAGE / STARFLEX	POLI-FLEX® IMAGE 4222 - 4275	TURBO PRINT 4036 MATT	ULTIMATE PRINT SOFT 4030/4032 MATT/4031 GLOSS	ULTIMATE PRINT MATT 4025	ULTIMATE PRINT SUPERSOFT 4033 MATT	ULTIMATE PRINT TRANSPARENT SOFT 4034 MATT	POLI-FLEX® 4010 BLOCKOUT	POLI-FLEX® 4015 / 4016	POLI-FLEX® 4600 / 4605	POLI-FLEX® 4655	POLI-FLEX® 4625 / 4626	POLI-FLEX® 4665 METALLIC	SUBLI-FLOCK 4675	SOLVENT-FLOCK 5901 / TUBITHERM PES				
TRANSFER CONDITIONS	Temperature (°C) Teplota	160	160	150	160	130	Standard 160 Nylon* 150	160	160	160	160	160	160	160	160	160	160	160	160	Standard 160 Nylon* 150	160	160	160	160	150	135	160	160	160	160	160	160	160	160	
	Pressure (bar) Tlak	2,5 3,0	2,5 3,0	2,0	2,5 3,0	2,5 3,0	2,5 3,0	2,0	2,0	2,0	2,0	2,5 3,0	2	3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0			
	Time (sec.) Cas	15	15	Pre-pressing 4 Second pressing 10 ^{xx}	15	10	3 4 5	5 5 10*	15	15	15	15	Pre-pressing 4 Second pressing 10 ^{xx}	25	15	15	15	15	15	15	15	3 4 5	5 5 10*	15	15	15	15	15	15	15	15	15	15		
	Sejmutí ochrané fólie Peel (Warm= W / Cold= C) W - zatepla / C za studena	W	W	W	W	W	W & C	W & C	W	W	W	W	W	C	C	C	C	W	W	W	C	W	W	W	W	C	W	C	W	W	W	W	W		
WASH CONDITIONS	Wash resistance (°C) Praní	80	60	40	80	40	60	40	60	40	40	60	40	60	60	60	60	40	60	60	40	80	60	40	60	40	40	40	60	60	60	40	90	60	40
	Tumble dry Sušička	●			●	●	●**		●	●		●		●	●	●	●	●	●	●	●		●	●	●	●	●	●	●	●	●	●	●	●	
	Dry cleaning Chemické čištění	●	●		●	●	●																												

x předlisování
xx druhé lisování

*POLI-FLEX® TURBO & TURBO PRINT
- předlisování 5 s
- lisování na nylon 5 s
- po odstranění PET lineru 10 s

** POLI-FLEX® TURBO TURBO PRINT
průmyslové sušičky až do 100 °C